

Dayscreen 5%

External Screens & Awnings



Application: • External Screens and Awnings

Characteristics: • Width: 2200mm (*selected colours) | 2750mm | 3200mm

Technical:

- Composition: 30% Polyester | 70% PVC
- Basketweave: 2x2
- Openness Factor: 5%
- Nominal Thickness ISO 2286-3: 0.82 mm +/- 5%
- Nominal Weight ISO 2286-2: 605 gsm +/- 5%
- Light Fastness: 6 (Bluescale) Tested to EN ISO 105
- Formaldehyde Free | Lead Free | Phthalate Free | VOC free
- Yarn Count ISO 7211/2: Warp 36 +/-% per 25.4mm | Weft 31 +/- % per 25.4mm
- Breaking Strength ISO 1421 Warp: 223 daN/5cm | Weft: 201 daN/5cm
- Tear Strength ISO 4674 Warp: 14.9 daN | Weft 11.8 daN
- Colour Fastness to Light ISO 105: B04: 8
- Mould Resistance ISO 846: A and B
- Printable

Protection:


- Fire Classification: Tested to NFPA 701 – 2010 (FR-USA) | DIN 4102 – 1 (B1 – DE)
- Greenguard and Greenguard Gold Accredited
- Oeko-Tex Certified
- UV Resistant
- Manufactured in accordance with: Management Quality System ISO 9001
- Manufactured in accordance with: Environmental Management System ISO 14001

Warranty: • 10 Years

Colour Range *



Dayscreen 5%



* Images representative only